

RADIATOR PAINT - HKL/HKLS



Application

For inside. For radiators conduits and metal objects. First pre spray the radiators lightly and then finish spray with only one paint layer. Stir well before use. Dust dry after 1 - 2 hours and repaintable after 24 hours. Process with brush, roller or airless, if necessary dilute with White Spirit or a low aromatic dilution. Wash hands well with soap after use.

Special advantages

Heat resistant, almost non-yellowing, fast drying.

Dilution

Ready for use, if needed with Special T. Appliances can be cleaned with Special T.

Processing

Apply with brush, roller or airless-spray. Do not process beneath 6°C and by an air humidity of > 80%.

Drying time

Within 1-2 hours dust dry. After 3-4 hours tack free. After 16 hours repaintable, dependent on temperature and air humidity.

Efficiency

Ca. 8 - 12 m²/kg, dependent on condition and suction of the substrate.

Degree of gloss

HKL = High gloss

HKLS = Satin gloss

Colour

White and tintable

Package

Cartons of 4x5 kg and cartons of 20x1 kg

Binder

A combi-resin on sunflower oil basis.

Pigment

Titanium dioxide and specialpigments

Solid matter content

Ca. 73 - 76 weight %

Specific gravity

Ca. 1.30 - 1.35 g/ml, 23°C

Viscosity

Ca. 1010 mPas, 23°C

Flash point

Ca. 40°C

Shelf life

1 year -Frost-free storage-

VOS

2004/42IIA (i) (600/500) Max. 320 g/ltr

Conveyance

KCA

