

PRE LAQUER - VL



Application

For interior and exterior. A half synthetic based primer, suitable for all substrates. Sand old paint layers well. Dust dry after 3-4 hours, trough hardened after 24 hours. Excellent sand able dry as well as wet. Dilute the varnish till max. 10% with white spirit for the prime coat. For the second coat max. 3%. The second layer can then serve as outdoor resistant satin gloss enamel for 1 year. Doesn't change and powder. Apply top coat with WHITE ENAMEL - WL only when the wood substrate contains less than 15% moist.

Special advantages

A Prime coat stays tough and elastic. Flow and covering power, also on the edges are unparalleled, contains no filler. Moisture controlling.

Dilution

Special T (low aromatic).

1e Layer: up to 4-6%

2e Layer: up to 3%

Appliances can be cleaned with Special T.

Processing

Apply with brush, roller or airless-spray. Do not process beneath 6°C and by an air humidity of > 80%.

Drying time

Within 2-3 hours dust dry. After ca. 24 hours repaintable, dependent on temperature and air humidity.

Efficiency

Ca. 6 - 10 m²/kg, dependent on condition and suction of the substrate.

Degree of gloss

Between mat and eggshell gloss

Colour

White and tintable

Package

Cartons of 4x5 kg.

Binder

Linseed oil alkyd resins.

Pigment

Titanium dioxide and specialpigments

Solid matter content

Ca. 75 - 80 weight %

Specific gravity

Ca. 1.40 - 1.45 g/ml, 23°C

Viscosity

Ca. 1000 mPas, 23°C.

Flash point

Ca. 36°C

Shelf life

1 year -Frost-free storage-

VOS

2004/42IIA (g) (450/350) Max. 346 g/ltr

Conveyance

KCA

